

Reinforced Extruded Rubber Lay Flat Fire Hose

COLORS:



General Applications:

- Specially designed for municipal fire departments, navies, petrochemical, nuclear plants, and other industrial services
- Superior nitrile/PVC rubber hose for use in supply and attack operations

Construction:

Made from circularly woven 100% high tenacity synthetic yarn, completely protected and locked-in by a tough, highly resistant synthetic nitrile rubber and PVC blend extruded through the weave and forming a single homogenous construction without the use of glues or adhesives.

Lining Properties – The tensile strength of the lining and cover shall not be less than 1,750 PSI (12,000 kPa), with an ultimate elongation of liner and cover not less than 450%.

Accelerated Aging – Lining specimens subjected to an exposure of 158°F ± 3.6°F, for a duration of 96 hours shall be conditioned as per ASTM D 573, Standard Test Method for Rubber – Deterioration in an Air Oven. Then, the specimens shall be tested to ASTM D4112, Standard Test Methods for Vulcanized Rubber and Thermoplastic Elastomers- Tension, Method A. Upon evaluation, the tensile and elongation properties of the liner shall not be less than 75% of their initial values.

Abrasion Resistance – As stated in National Fire Protection Association (NFPA) 1961, Underwriters Laboratories (UL) 19 and Factory Mutual Approval Standard (FM) 2111, hose shall withstand 1 1/2 times the service test pressure without rupturing or breaking any thread in the jacket or reinforcement after 300 cycles of abrasion for a single jacketed hose. Hose assembly shall also not leak or burst after 3,000 cycles by an abrasion wheel.



Service Temperature Range:
-4°F (-20°C) to +176°F (+80°C)

BECAUSE WE CONTINUALLY EXAMINE WAYS TO IMPROVE OUR PRODUCTS, WE RESERVE THE RIGHT TO ALTER SPECIFICATIONS OR DISCONTINUE PRODUCTS WITHOUT PRIOR NOTICE.

Features and Advantages:

- Resistant to petroleum, chemicals and abrasion.
- Underwriters Laboratories (UL) 19 and Underwriters Laboratories of Canada (ULC) – S511-14 Certified*.
- Reliable and robust.
- Lightweight and flexible.
- Fast deployment and retrieval.
- Meets or exceeds National Fire Protection Association (NFPA) 1961 Standard on Fire Hose (current edition).
- ISO 9001 - ARMTEX® Jafrib® fire hose products are manufactured in a registered facility in Barcelona, Spain.
- 10-year warranty.

Packaging:

Available in 25', 50' and 100' lengths.

Uncoupled Hose

Nominal Specifications

Part Number*	Size (in)	Color	Bowl Size (in)	Service Test (psi)	Proof Test (psi)	Burst Test (psi)	Available Lengths (ft)	Weight Uncoupled (lbs/ft)
50H1RY-XXX	1†	Yellow	1 3/16	300	600	900	25/50/100	0.13
50H15RY-XXX	1 1/2	Yellow	1 3/4	300	600	900	25/50/100	0.30
50H175RY-XXX	1 3/4	Yellow	2 1/16	300	600	900	25/50/100	0.32
50H2RY-XXX	2	Yellow	2 9/32	300	600	900	25/50/100	0.38
50H25RY-XXX	2 1/2	Yellow	2 13/16	300	600	900	25/50/100	0.45
50H3RY-XXX	3	Yellow	3 5/16	300	600	900	25/50/100	0.64
50H4RY-XXX	4	Yellow	4 9/32	250	500	750	25/50/100	0.81
50H5RY-XXX	5	Yellow	5 3/8	225	450	675	25/50/100	0.94
50H6RY-XXX	6	Yellow	6 3/8	200	400	600	25/50/100	1.28
50H15RR-XXX	1 1/2	Red	1 3/4	300	600	900	25/50/100	0.30
50H175RR-XXX	1 3/4	Red	2 1/16	300	600	900	25/50/100	0.32
50H2RR-XXX	2	Red	2 9/32	300	600	900	25/50/100	0.38
50H25RR-XXX	2 1/2	Red	2 13/16	300	600	900	25/50/100	0.45
50H3RR-XXX	3	Red	3 5/16	300	600	900	25/50/100	0.64
50H4RR-XXX	4	Red	4 9/32	250	500	750	25/50/100	0.81
50H5RR-XXX	5	Red	5 3/8	225	450	675	25/50/100	0.94
50H6RR-XXX	6	Red	6 3/8	200	400	600	25/50/100	1.28

*XXX = Available Lengths

† 1" Jafrib is a dark yellow

BECAUSE WE CONTINUALLY EXAMINE WAYS TO IMPROVE OUR PRODUCTS, WE RESERVE THE RIGHT TO ALTER SPECIFICATIONS OR DISCONTINUE PRODUCTS WITHOUT PRIOR NOTICE.

Reinforced Extruded Rubber Lay Flat Fire Hose

Assemblies

Nominal Specifications										
Part Number*	Size (in)	Color	Coupling Size (in)	Coupling Type	Bowl Size (in)	Service Test (psi)	Proof Test (psi)	Burst Test (psi)	Available Lengths (ft)	Weight Uncoupled (lbs/ft)
JR150RXXX-NH150	1 1/2	Red	1 1/2	NST	1 3/4	300	600	900	25/50/100	0.30
JR150RXXX-NP150	1 1/2	Red	1 1/2	NPSH	1 3/4	300	600	900	25/50/100	0.30
JR175RXXX-NH150	1 3/4	Red	1 1/2	NST	2 1/16	300	600	900	25/50/100	0.32
JR175RXXX-NP150	1 3/4	Red	1 1/2	NPSH	2 1/16	300	600	900	25/50/100	0.32
JR250RXXX-NH250	2 1/2	Red	2 1/2	NST	2 13/16	300	600	900	25/50/100	0.45
JR300RXXX-NH250	3	Red	2 1/2	NST	3 5/16	300	600	900	25/50/100	0.64
JR400RXXX-SZ400	4	Red	4	STORZ	4 9/32	250	500	750	25/50/100	0.81
JR500RXXX-SZ500	5	Red	5	STORZ	5 3/8	225	450	675	25/50/100	0.94
JR600RXXX-SZ600	6	Red	6	STORZ	6 3/8	200	400	600	25/50/100	1.28
JR100YXXX-NH100	1†	Yellow	1	NST	1 3/16	300	600	900	25/50/100	0.13
JR100YXXX-NP100	1†	Yellow	1	NPSH	1 3/16	300	600	900	25/50/100	0.13
JR150YXXX-NH150	1 1/2	Yellow	1 1/2	NST	1 3/4	300	600	900	25/50/100	0.30
JR150YXXX-NP150	1 1/2	Yellow	1 1/2	NPSH	1 3/4	300	600	900	25/50/100	0.30
JR175YXXX-NH150	1 3/4	Yellow	1 1/2	NST	2 1/16	300	600	900	25/50/100	0.32
JR175YXXX-NP150	1 3/4	Yellow	1 1/2	NPSH	2 1/16	300	600	900	25/50/100	0.32
JR200RXXX-NH150	2	Red	1 1/2	NST	2 9/32	300	600	900	25/50/100	0.38
JR200YXXX-NH150	2	Yellow	1 1/2	NST	2 9/32	300	600	900	25/50/100	0.38
JR250YXXX-NH250	2 1/2	Yellow	2 1/2	NST	2 13/16	300	600	900	25/50/100	0.45
JR300YXXX-NH250	3	Yellow	2 1/2	NST	3 5/16	300	600	900	25/50/100	0.64
JR400YXXX-SZ400	4	Yellow	4	STORZ	4 17/32	250	500	750	25/50/100	0.81
JR500YXXX-SZ500	5	Yellow	5	STORZ	5 3/8	225	450	675	25/50/100	0.94
JR600YXXX-SZ600	6	Yellow	6	STORZ	6 3/8	200	400	600	25/50/100	1.28

*XXX = Available Lengths

*UL 19 and CAN/ULC-S511-14 certified models – All except the 1" and the 6"

† 1" Jafrib is a dark yellow

BECAUSE WE CONTINUALLY EXAMINE WAYS TO IMPROVE OUR PRODUCTS, WE RESERVE THE RIGHT TO ALTER SPECIFICATIONS OR DISCONTINUE PRODUCTS WITHOUT PRIOR NOTICE.